

Fig.1




Fig.2




Fig.3




Fig.4




Fig.5

Kind	Red paint RT				Yellow paint YT				Blue paint BT			
	L*	a*	b*		L*	a*	b*		L*	a*	b*	
1st	58.19	20.34	14.34		77.84	-3.33	40.68		48.61	-9.52	-39.99	
2nd	58.20	20.41	14.36		77.92	-3.42	40.53		48.70	-9.62	-40.12	
3rd	58.13	20.40	14.31		78.03	-3.43	40.56		48.67	-9.56	-40.03	
Mean	58.18	20.38	14.34		77.93	-3.39	40.59		48.66	-9.57	-40.05	
	ΔL^*	Δa^*	Δb^*	ΔE	ΔL^*	Δa^*	Δb^*	ΔE	ΔL^*	Δa^*	Δb^*	ΔE
1st	0.02	-0.04	0.01	0.05	-0.09	0.07	0.09	0.14	-0.05	0.05	0.06	0.09
2nd	0.03	0.02	0.02	0.04	-0.01	-0.03	-0.06	0.07	0.04	-0.05	-0.08	0.10
3rd	-0.04	0.02	-0.02	0.05	0.10	-0.04	-0.03	0.11	0.01	0.01	0.02	0.02
Mean				0.05				0.11				0.07